



Surface Mount Supplies

Conductive 2666 Pressure-Sensitive Cover Tape

Technical Data – January 2000

Product Description


3M™ Conductive 2666 Pressure-Sensitive Cover Tape is a transparent, conductive polyester film tape with a synthetic, room temperature, pressure-sensitive adhesive [PSA] zone along each edge. 2666 Cover Tape has been designed to seal electrical and electronic components into 3M's family of Polycarbonate Carriers. It may also work well with other embossed carrier tapes.

Construction

Backing
Transparent polyester film

Adhesive
Pressure-sensitive, synthetic polymer

Inner Face
Transparent, conductive, polyester film



Available Widths

2666 Cover Tape is available in the standard sizes listed below, with adhesive exposed only along the edges. All 2666 Cover Tape is supplied in 200 meter, splice-free rolls.

Standard Sizes, mm Widths									
Carrier	8	12	16	24	32	44	56	72	88
Cover Tape	5.4	9.3	13.3	21.3	25.5	37.4	49.4	66.5	82.4
Adhesive Exposure each edge	0.67	0.8	1	1	1	1	1	2.5	2
Roll Length (m)	200	200	200 500	200 500	200 500	200 500	200 500	200 500	200 500

Packaging Options

2666 PSA Cover Tape is available in standard or clean-room compatible packaging.

Standard



Product is provided on a plastic core, packaged with high density paper wafer inserts and a centering core in a single polyethylene bag, and is placed between two endcaps in a cardboard carton.

Cleanroom Compatible

Product is standard but packaged in two polyethylene bags as opposed to one. This format allows the cover tape to be used and stored in a cleanroom in a bag that has not had direct contact with the cardboard carton.

Typical Adhesive Properties

Conductive 2666 Pressure-Sensitive Cover Tape has a simple process window. Desirable initial peel force values can be achieved through the application of adequate pressure to the non-adhesive surface of the cover tape over the adhesive stripes with a reciprocating shoe, or compliant roller mechanism. The following charts depict the typical room temperature and aging characteristics of 2666 Cover Tape after sealing to 3M™ Conductive 3000 Polycarbonate Carrier.



Note: The technical information and data presented here should be considered representative or typical only, and should not be used for specification purposes.

Graph Notes

Notes: The graphs in this document represent sealing performance attained under the conditions specifically stated in the sealing parameters section of the charts. Pressure is the indicated gauge pressure used to achieve the seals, and may vary among sealing equipment manufacturers. The use of a different sealing mechanism, i.e., reciprocating vs. roller, may have an effect upon the performance obtained under otherwise identical conditions due to differences in pressure or pressure distribution. The use of heat is specifically not recommended.

All data presented are representative of peeling studies conducted according to the requirements of the current ANSI/EIA-481 Standard. Sealed samples used in these studies were stored under the conditions noted, wound on 330mm diameter reels to simulate typical production use. Samples being tested at elevated temperature and humidity were permitted a minimum equilibration period of one hour at room temperature prior to testing to simulate actual use conditions.

Sealing Parameters:

Cover Tape: Conductive 2666 Cover Tape, 21.3mm
Carrier: Conductive 3000 Carrier Tape, 24mm
Sealing Mode: Continuous (Rubber Pressure Roller)
Pressure: 3 bar (42 psig)
Speed: 1.5 linear meters/minute
Temperature: Room Temperature, $\approx 23^{\circ}\text{C}$ (73°F)

Adhesive Properties

The synthetic adhesive used in the construction of 3M Conductive 2666 Pressure-Sensitive Cover Tape has been engineered to provide long term resistance to thermal degradation, even when exposed to environmental extremes such as the storage conditions depicted in the charts in this publication.

Storage Conditions

3M Conductive 2666 Pressure-Sensitive Cover Tape should be stored indoors, in its original packaging, in a controlled climate environment not exceeding 35°C (95°F) and 70% relative humidity. The product should be protected from direct sunlight and should be used on a “first-in, first-out” basis.

Shelf Life

It is recommended that 3M Conductive 2666 Pressure-Sensitive Cover Tape be used within 3 years from the date of manufacture when stored according to the recommended storage conditions.

Conductive 2666 Pressure-Sensitive Cover Tape

Description	Units	Typical Performance	Test Notes	Test Method
Material Properties	Backing Type Adhesive Type Sealing Temp	Polyester PSA Room Ambient	1	
Physical Properties	Tensile Strength Elongation Transparency Thickness	N/mm Width % % mm (in)	7.0 150 80 .061 (.0024)	2 ATSM-D3759 3 ASTM-D3652
Electrical Properties	Resistivity (Back Side) Resistivity (Component Side)	Ohms/sq Ohms/sq	Non-Conductive 10 ⁵	4 4 ASTM-D257 ASTM-D257
Product Format	Core Type Core Inner Diameter Roll Diameter Roll Length	Material mm (in) mm (in) m (yd)	Plastic 76.2 (3.0) 152 (6.0), 216 (8.5) 200 (218), 500 (546.5)	

Note: The technical information and data presented here should be considered representative or typical only, and should not be used for specification purposes.

Test Notes

1. The application of heat to seal PSA cover tapes is specifically not recommended. Pressure in the range of 100 to 500 p.s.i. is sufficient to seal PSA adhesives.
2. Tensile tests are conducted at 21°C (70°F), 50% RH, in the machine direction of the polyester film.
3. Optical properties are measured using light transmission.
4. Resistivity is measured at room ambient temperature. Component side resistivity specification $1 \times 10^4 \leq R_s \leq 1 \times 10^7$. Measurement technique: 4-bar probe with Keithley 237 Source Measuring Unit.

Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-666-8273. Address correspondence to: 3M Electronic Handling & Protection Division, 6801 River Place Blvd., Austin, TX 78726-9000. Our fax number is 1-800-826-8893.

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability.

This product will be free from defects in material and manufacture for a period of one year from the date of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any loss or damage arising from this 3M product, whether direct, indirect, special, incidental or consequential regardless of the legal theory asserted.



Electronic Handling & Protection Division Surface Mount Supplies

6801 River Place Blvd.
Austin, TX 78726-9000
800/MMM TAPE (800/666 8273)
FAX 800/826-8893
www.3M.com/ehpd



40% Pre-consumer waste paper
10% Post-consumer waste paper

Litho in USA.

© 3M IPC 2000 80-6111-0106-6